

Technical specification

Quality Abdeckpapier Standard braun (400) 50 g/m²

S0014 MG plain

Substance g/qm 48 - 52 DIN EN ISO 536:2012

Tensile strength md N/15mm > 22 DIN EN ISO 1924-2:2009

Tensile strength cd N/15mm > 11 DIN EN ISO 1924-2:2009

cd / md relation % > 40

Breaking length md mtr. > 3.100 DIN EN ISO 1924-2:2009

Breaking length cd mtr. > 1.600 DIN EN ISO 1924-2:2009

Breaking length average mtr. > 2.350 DIN EN ISO 1924-2:2009

Burst strength abs. kPa > 65 DIN EN ISO 2758:2014

Burst strength rel. kg/qcm > 1,3 DIN EN ISO 2758:2014

Air resistance (Bendtsen) ml/min 200 - 600 DIN 53120-1:2018

Sizing COBB 60 g/qm 15 - 25 DIN EN ISO 535:2014

Since the end use of the paper is beyond our direct controll, we expect that the customer will satisfy themselves that the

paper is suitable for that end use. Unless specifically negotiated, we reserve the right to use raw materials from more than

one source whilst still maintaining a commercial match within the terms of this specification.

Above mentioned values will be checked on regular basis by our process control. This

specification doesn't release the

buyer from a thorough entrance control.

Validity of this specification - maximum twelve months from date of printing.

Issued author Dieter Schürmann/ Quality Manager

Date of printing Wednesday, 17. June 2020