

Mixing Instructions



FlexiDry[®]
Global Ltd

INNOVATORS IN SCREED SCIENCE

Mixing of Material

Materials should be mixed in a forced action mixer such as a screed pump or pan mix. The correct dosage of FlexiDry should be dispersed in a water bucket and added to the correct sand and cement grades. Mixing time should be approximately 2 minutes, ensuring a good distribution of product and water, adjusted to facilitate trowelling. See dosage chart above for FlexiDry quantities. Materials to be read in conjunction with BS8204:1 2003 and relevant codes of practice.

Dosage

F1 (7 days): 175ml of FlexiDry per 25kg of Cement

F2 (14 days): 125ml of FlexiDry per 25kg of Cement

F3 (21 days): 85ml of FlexiDry per 25kg of Cement

