



## Wet-Pour Depths and Critical Fall Heights (CFH) Page 120

### Sub Base - MOT Type 1 Stone



CFH 1.35m

#### 40mm

40mm comprises of a 15mm wearing course layer and a 25mm base layer. This offers a sufficient surface for equipment with a CFH of 1.35m or less when installed on to Mot Type 1 stone.



CFH 1.75m

#### 50mm

50mm comprises of a 15mm wearing course layer and a 35mm base layer. This offers a sufficient surface for equipment with a CFH of 1.75m or less when installed on to Mot Type 1 stone.



CFH 2.30m

#### 60mm


60mm wetpour [playground surfacing](#) comprises of a 15mm wearing course layer and a 45mm base layer. This offers a sufficient surface for equipment with a CFH of 2.30m or less when installed on to Mot Type 1 stone.



CFH 2.80m

#### 80mm

80mm comprises of a 15mm wearing course layer and a 65mm base layer. This offers a sufficient surface for equipment with a CFH of 2.80m or less when installed on to Mot Type 1 stone.



CFH 3.00m or more

#### 100mm

100mm [wetpour](#) comprise of a 15mm EPDM wearing course layer and an 85mm SBR base layer. This offers a sufficient surface for equipment with a CFH of 3.00m or more when installed on to Mot Type 1 stone.

*Please use this table for guide purposes only. CFH ratings may vary depending on the sub base they are laid over. We would be only too pleased to clarify your specific site requirements.*

