



Herculan SO sports surfaces are eco-friendly, seamless and cushioned Multi Purpose floors with point elastic properties.

Herculan SO sports surfaces meet all the latest European Standards for multi purpose indoor sports surfaces, the EN 14904:2006. **Herculan SO** quality sports floors are accredited with the CE Certificate of Conformity.

Herculan SO system passes the German AgBB/DIBt emission test and is rated as safe for indoor building materials.

The seamless surface of the **Herculan SO** system is non-porous, therefore hygienic and easy to clean. **Herculan SO** systems provide the optimum slide and slip resistance required in today's sports. Due to its good mechanical strength and elastic properties of the Herculan ST 100 thickness layer and the excellent wear resistance of its Herculan PU 145 or Herculan PU 100W top-layer, this tough and durable sports surface is an economic solution for multi sports facilities.

All Herculan Sports Surfaces are easy to maintain and can be resurfaced quickly and economically when required.



www.herculan.com





Types of Sports Surface	Multi-purpose point-elastic indoor sports surface.
Aim	Suitable for all indoor sports and multi functional use, see Herculan Systems Selection Chart.
Description of the Sports Surface	2 or 3 mm of coated polyurethane layer on bonded rubber granulate sub-base layer.

HERCULAN SO SYSTEM PROPERTIES

Athlete Surface Interaction

System	Vertical Deformation [EN 14809 – DIN 18032-2]	Force Reduction [EN 14808 – DIN 18032-2]	Energy Restitution [EN 14808]
Herculan SO 4 + 2	1 mm	13 %	68 %
Herculan SO 5 + 2	1 mm	18 %	69 %
Herculan SO 6 + 2	1 mm	22 %	69 %
Herculan SO 7 + 2	1 mm	25 %	67 %
Herculan SO 8 + 2	1 mm	28 %	67 %
Herculan SO 9 + 2	1 mm	32 %	66 %
Herculan SO 10 + 2	1.5 mm	35 %	62 %
Herculan SO 10 + 3	1.5 mm	33 %	61 %
Herculan SO 12 + 3	1.5 mm	39 %	60 %

System Properties of the Sports Surface

Vertical Ball Behavior [EN 12235 – DIN 18032-2]	99 %
Compression Set [ASTM D-395-B]	1.9 %
Compression Strength [N/S1.1]	> 400 N/mm ² [> 400 MPa]
Resistance to Impact [EN 1517-1999]	> 8 Nm
Resistance Against Static Load [24 hours]	15 kg/cm ²
Resistance to Indentation [EN 1516]	< 0.11 mm
Resistance to a Rolling Load [EN 1569:1999]	> 1500 N, < 0.5 mm
Resistance to Fire [DIN 51960]	Not flammable – Class 1
Resistance to Fire [BS 476 Part 7:1997]	Not flammable – Class 3
Resistance to Fire [EN ISO 11925:2002 & 9239-1:2002]	B _{FL} – S1
Resistance to Stubbed and Burning Cigarettes [EN 1399]	Resistant. No Damage
Formaldehyde Emission [EN 717-1]	Class E1. No Formaldehyde
AgBB: Health-related Evaluation of Emissions of Volatile Organic Compounds [VOC and SVOC]	Approved for Indoor usage

Properties of the Herculan ST 100 Base Layer

Surface Hardness [DIN 53505, EN ISO 868]	Shore A = 84
Tensile Strength [EN ISO 527-1, DIN 54455]	7 N/mm ² [7 MPa]
Elongation at Break [EN ISO 527-1, DIN 54455]	> 120 %
Tear Resistance [DIN 53515]	20 N/mm

Properties of the Herculan PU 145/PU 100W Surface Layer

Surface Texture [N/F 12.1 Macro, Micro, Porosity]	Fine, Polished, Closed
Surface Color	See Herculan Color Chart
Resistance to Wear [EN ISO 5470-1, ASTM C-501]	Taber H18 1 kg 1000 cycles 165 mg
Gloss [EN ISO 2813]	3 – 6 %
Friction [EN 13046-4]	Dry 90 at 20°C
Friction [EN 14837 Leroux]	Dry 0.7 at 20°C
	Wet 0.4 at 20°C
	Dry 0.4 at 20°C
	Wet 0.2 at 20°C
Sliding Qualities [N/F 6.1]	8 [Excellent]
Light [Color] Fastness [DIN 54004]	0.1 – 0.3 [Color dependent]
Specular [light] Reflectance [EN 13745]	

Herculan Sports Surfaces B.V.

Energieweg 6, 4231 DJ Meerkerk, P.O. Box 46, 4230 BA Meerkerk, The Netherlands.
 Phone : +31 183 35 47 00 • Fax : +31 183 35 47 40 • E-mail : info@herculan.com • www.herculan.com